

Skill

Ecopelle / Artificial leather Cat. A

Composizione/ Composition

69% PVC
30% CO/PES
1% PU

Abrasione/Abrasion (Martindale)

50.000 cicli/cycles
EN ISO 5470-2

Solidità colori alla luce Colour fastness to light


6/7 EN ISO 105 B02

Solidità colori allo sfregamento Colour fastness to rubbing

secco _ dry: 5
umido _ wet: 5
EN ISO 105 X12

Resistenza al fuoco/Flame Retardant


BS 5852-1 ▪ EN 1021-1/2 ▪ ÖNORM B 3825 ▪
UNI 9175 classe 1IM ▪ US Cal. TB 117-2013




SKL 3




SKL 26




SKL 6




SKL 28




SKL 30



SKL 13




SKL 32



SKL 22



SKL 36



SKL 24

Disponibile su richiesta in 37 colori
Scheda tecnica completa > [clicca qui](#).

Available on demand in 37 colours.
Complete technical schedule > [click here](#).

cizeta